

检 测 报 告
TEST REPORT

报告编号 (No.): UTS24120047R05R2 报告日期 (Report Date): 2025/03/19

委托单位/Client : 北京双龙盛电气制造有限公司
Beijing Shuanglongsheng Electric Manufacturing Co., LTD

地 址/Address : 北京市通州区台湖镇经略天则南区 2.19
2.19, Tianze South District, Taihu Town, Tongzhou District, Beijing

以下样品信息由申请人提供及确认:

The sample(s) information below is/are provided and confirmed by client:

样品名称/Sample Name : 不锈钢槽式电缆桥架/Stainless steel trough cable bridge

型 号/Model	: 50*50	400*100	800*100
	100*50	400*150	800*150
	100*75	400*200	800*200
	100*100	500*100	1000*100
	150*75	500*150	1000*200
	150*100	500*200	1200*100
	200*100	600*100	1200*200
	200*150	600*150	1400*100
	300*100	600*200	1400*200
	300*150	700*100	1400*350
	300*200	700*150	
		700*200	

生产单位地址 : 江苏省扬中市开发区园博大道北 100 米
/Production unit address 100 meters north of Yuanboda Road, Yangzhong Development Zone, Jiangsu Province

测试标准/Test standard : JB/T 10216-2013 《电控配电用电缆桥架》《企业技术要求》
JB/T 10216-2013 "Electric Control distribution Cable Bridge"
"Enterprise Technical Requirements"

联系人/Contact person : 陈龙/Chen Long

接样日期/Receiving Date : 2024/12/20

签 发
Approved by

樊建红 授权签字人

审 核
Reviewed by
周伟编 制
Prepared by
王彭

Page 1 of 11

This Test Report is issued by the Company subject to its General Conditions of Service printed overleaf or available on request. Attention is drawn to the limitations of liability, indemnification and jurisdictional policies defined therein. The results shown in this Test report refer only to the sample(s) tested unless otherwise stated. This test report shall not be reproduced, except in full, without written approval of the Company. 本报告按本公司所制定之通用服务条款所编制发放。请注意本报告首页背面之此条款，本公司之义务、免责、管辖权均有明确规定，该条款也可向本公司索取。除非另有说明，本报告仅对来样负责，未经许可，不得部分复制本报告。

江苏省优联检测技术服务有限公司

地址: 苏州市吴中区越溪街道北官渡路50号3幢 215021

电话 (Tel): +0512-66358200

UNITED TESTING SERVICES (JIANGSU) CO., LTD.

Address: Building 3, No.50 Beiguandu Road, Wuzhong Zone, Suzhou, Jiangsu, China, 215021

传真 (Fax): +0512-66358088

----- www.uts.com.cn -----

检 测 报 告
TEST REPORT

报告编号 (No.): UTS24120047R05R2 报告日期 (Report Date): 2025/03/19

结果总结/Summary of Result(s):

样品名称 Sample Name	项目 Item(s)		判定 Determine	页码 Page Number
不锈钢槽式电缆 桥架/Stainless steel trough cable bridge	1	外观及尺寸精度检测 Appearance and dimension accuracy inspection	符合/PASS	3
	2	机械载荷试验 Mechanical load test	符合/PASS	4
	3	撞击试验 Bump test	符合/PASS	5
	4	人工气候试验——交变湿热试验 24h Artificial climate test -- alternating humid heat test 24h	符合/PASS	6-7
	5	人工气候试验-盐雾试验 48h Artificial climate test - salt spray test 48h	符合/PASS	8-9
	6	保护电路连续性（接地） Protection circuit continuity (ground connect)	符合/PASS	9-10
	7	防护等级 IP30 Protection class IP30	符合/PASS	10-11

.....接下页/ To be continued.....

检 测 报 告
TEST REPORT

报告编号 (No.): UTS24120047R05R2 报告日期 (Report Date): 2025/03/19

一、外观及尺寸精度检测/Appearance and dimension accuracy inspection

1、测试标准/Test standard

依客户要求要求进行试验，详见测试条件。/The test was/were carried out according to client's requirement, details was/are given in the test condition(s).

2、测试日期/Test Date

2024/12/23

3、测试条件/Test Condition


目视/Visual

4、测试结果/Test Result(s)

样品编号 Sample No.	结果 Result	判定依据 Judgment basis	判定 Determine
5-1	无肉眼可观察到的缺陷，长度为 2m，槽体宽度为 20cm，高度为 10cm。/There are no visible defects, the length is 2m, the width of the tank is 20cm, and the height is 10cm.	表面防护层外观：从某一距离去观察，在有效表面上应没有肉眼可观察到的缺陷； 长度:±2 宽度:槽体-2.5 高度:±2.5 /The appearance of the surface protective layer: observed from a certain distance, there should be no defects observable by the naked eye on the effective surface; Length :±2 Width: tank -2.5 Height :±2.5	符合/PASS

备注/Remark: 判定限值依客户要求。/The prescribed limit(s) is/are according to client's requirement.

5、测试照片/Test Photo(s)

	
外观/Appearance	尺寸/Dimension

检 测 报 告
TEST REPORT

报告编号 (No.): UTS24120047R05R2 报告日期 (Report Date): 2025/03/19

二、机械负载试验/Mechanical load test

1、测试标准/Test standard

依客户要求进行了试验，详见测试条件。/The test was/were carried out according to client's requirement, details was/are given in the test condition(s).

2、测试日期/Test Date

2024/12/24

3、测试条件/Test Condition

跨距/Span: 1m


承载力/Bearing capacity: 1000N/m

4、测试结果/Test Result(s)

样品编号 Sample No.	结果 Result	判定依据 Judgment basis	判定 Determine
5-2	绕度值/Winding value: 0	绕度值/Winding values≤10	符合/PASS

备注/Remark: 判定限值依客户要求。/The prescribed limit(s) is/are according to client's requirement.

5、测试照片/Test Photo(s)



检 测 报 告
TEST REPORT

报告编号 (No.): UTS24120047R05R2 报告日期 (Report Date): 2025/03/19

三、撞击试验/Bump test

1、测试标准/Test standard

GB/T 2423.55-2006 《电工电子产品环境试验 第 2 部分：试验方法 试验 Eh：锤击试验》/Environmental testing for electric and electronic products--Part 2 : Test methods--Test Eh: hammer tests

2、测试日期/Test Date

2024/12/26

3、测试条件/Test Condition


在长度为 250mm±5mm 的三个试品分别做底部和两个侧边的撞击试验，撞击位置为中部，撞击能量为 10J，次数为各一次。/Bump tests were conducted on the bottom and two sides of the three samples with a length of 250mm±5mm, respectively. The bump position was the middle, the bump energy was 10J, and the number of times was once.

4、测试结果/Test Result(s)

样品编号 Sample No.	结果 Result	判定依据 Judgment basis	判定 Determine
5-3	无变形和裂纹。/No deformation and crack.	不应出现影响安全使用的变形和裂纹。 /There should be no deformations and cracks that would affect safe use.	符合/PASS

备注/Remark: 判定限值依客户要求。/The prescribed limit(s) is/are according to client's requirement.

5、测试照片/Test Photo(s)



检测报告

TEST REPORT

报告编号 (No.): UTS24120047R05R2 报告日期 (Report Date): 2025/03/19

四、人工气候试验——交变湿热试验 24h/Artificial climate test -- alternating humid heat test 24h

1、测试标准/Test standard

GB/T 2423.4-2008 《电工电子产品环境试验 第2部分：试验方法 试验 Db 交变湿热（12h+12h 循环）》
/Environmental testing for electric and electronic products - Part 2: Test method - Test Db: Damp heat, cyclic (12h+12h cycle)

2、测试日期/Test Date


2024/12/24-2024/12/26

3、测试仪器/Test Equipment

设备名称 Test Equipment	设备编号 Equipment Number	校准有效期 Calibration Period of Validity
高低温交变湿热试验箱 High and low temperature alternating wet heat test chamber	R-1-089	2025/11/21

4、测试条件/Test Condition

相对湿度 95%，温度范围：25℃~44℃，1 个循环 24h。/Relative humidity 95%, temperature range: 25℃~44℃, 1 cycle 24h.



检 测 报 告
TEST REPORT



报告编号 (No.): UTS24120047R05R2 报告日期 (Report Date): 2025/03/19

5、测试结果/Test Result(s)

样品编号 Sample No.	结果 Result	判定依据 Judgment basis	判定 Determine
5-4	试验后，桥架表面防护层光泽未变暗，颜色未变化，无腐蚀点。/After the test, the gloss of the protective layer on the bridge surface did not darken, the color did not change, and there was no corrosion point.	24h 交变湿热试验后，允许桥架表面防护层光泽稍变暗，颜色稍退但无腐蚀点。/After 24h alternating wet heat test, the gloss of the protective layer on the surface of the bridge is allowed to darken slightly, and the color is slightly faded but there is no corrosion point.	符合/PASS

备注/Remark: 判定限值依客户要求。/The prescribed limit(s) is/are according to client's requirement.

6、测试照片/Test Photo(s)

	
测试前/Before test	测试中/During test
	
测试设备/Test equipment	测试后/After test

检 测 报 告
TEST REPORT

报告编号 (No.): UTS24120047R05R2 报告日期 (Report Date): 2025/03/19

五、人工气候试验-盐雾试验 48h/Artificial climate test - salt spray test 48h

1、测试标准/Test standard

GB/T 2423.17-2008 《电工电子产品环境试验 第2部分: 试验方法 试验 Ka: 盐雾》/Environmental testing for electric and electronic products - Part 2: Test method - Test Ka: Salt mist

2、测试日期/Test Date

2024/12/23-2024/12/25

3、测试仪器/Test Equipment

设备名称 Test Equipment	设备编号 Equipment Number	校准有效期 Calibration Period of Validity
盐雾腐蚀试验箱 Salt spray corrosion test chamber	R-1-079	2025/11/25

4、测试条件/Test Condition

环境温度/Environment Temperature : (23±2)℃
环境湿度/Environment Humidity : (50±5) %RH
试验温度/Test Temperature : (35±2) °C
盐水浓度/Medium : (5±1) % NaCl
pH 值/pH Value : 6.5~7.2
盐雾沉降率/Quantity of Fog : 1.0~2.0 mL/80cm²·h
持续时间/Duration : 48 h

5、测试结果/Test Result(s)




样品编号 Sample No.	结果 Result	判定依据 Judgment basis	判定 Determine
5-5	桥架表面光泽有变化, 无腐蚀点。 /The surface gloss of the bridge has changed, and there is no corrosion point.	经 48h 盐雾试验后, 桥架表面光泽允许有变化但无腐蚀点。/After 48h salt spray test, the surface gloss of the bridge is allowed to change but there is no corrosion point.	符合/PASS

备注/Remark: 判定限值依客户要求。/The prescribed limit(s) is/are according to client's requirement.

检 测 报 告
TEST REPORT

报告编号 (No.): UTS24120047R05R2 报告日期 (Report Date): 2025/03/19

6、测试照片/Test Photo(s)

	
测试前/Before test	测试中/During test
	/
测试后/After test	/

六、保护电路连续性（接地）/Protection circuit continuity (ground connect)

1、测试标准/Test standard

依客户要求进行试验，详见测试条件。/The test was/were carried out according to client's requirement, details was/are given in the test condition(s).

2、测试日期/Test Date

2024/12/30

3、测试结果/Test Result(s)


样品编号 Sample No.	结果 Result	判定依据 Judgment basis	判定 Determine
5-6	有可靠的电气连接并接地。/There is a reliable electrical connection and ground.	应有可靠的电气连接并接地/There should be a reliable electrical connection and ground	符合/PASS

备注/Remark: 判定限值依客户要求。/The prescribed limit(s) is/are according to client's requirement.

检 测 报 告
TEST REPORT

报告编号 (No.): UTS24120047R05R2 报告日期 (Report Date): 2025/03/19

4、测试照片/Test Photo(s)



七、防护等级 IP30/Protection class IP30

1、测试标准/Test standard

GB/T 4208-2017 《外壳防护等级 (IP 代码)》/Degrees of protection provided by enclosure(IP code)

2、测试日期/Test Date

2024/12/26

3、测试仪器/Test Equipment

设备名称 Test Equipment	设备编号 Equipment Number	校准有效期 Calibration Period of Validity
IP3X 试验探棒 IP3X test probe	R-1-591	2025/04/22

4、测试条件/Test Condition

用直径为 2.5mm 的试验棒，对试品外壳施加 $3\pm 0.3\text{N}$ 的力。/Using a test rod with a diameter of 2.5mm, a force of $3\pm 0.3\text{N}$ is applied to the test casing.

5、测试结果/Test Result(s)

样品编号 Sample No.	结果 Result	判定依据 Judgment basis	判定 Determine
5-7	试验过程试验棒未进入壳内。/The test rod did not enter the shell during the test.	试验过程试验棒不得进入壳内。/The test rod shall not enter the shell during the test.	符合/PASS


备注/Remark: 判定限值依客户要求。/The prescribed limit(s) is/are according to client's requirement.

检 测 报 告

TEST REPORT

报告编号 (No.): UTS24120047R05R2 报告日期 (Report Date): 2025/03/19

6、测试照片/Test Photo(s)



测试中/During test

此报告代替之前 2025/01/02 发出的报告 UTS24120047R05R1，特此声明报告 UTS24120047R05R1 作废。

This report replaces the report UTS24120047R05R1 that was issued on 2025/01/02, we hereby declare that the report UTS24120047R05R1 is invalid.

.....报告结束/End of Report.....

本报告中结果仅作为科研、教学或内部质量控制之用。

Test results in this report are only used for scientific research, teaching and internal quality control.